

<b>Bottom shell bushing</b>	
<b>Chemical composition</b>	
<b>Results of elements</b>	
<b>Cu %</b>	81,130
<b>Sn %</b>	9,140
<b>Pb %</b>	9,150
<b>Zn %</b>	0,07
<b>Ni %</b>	0,270
<b>Fe %</b>	0,020
<b>Al %</b>	0,000
<b>Mn %</b>	0,000
<b>Sb %</b>	0,170
<b>P %</b>	0,040
<b>S %</b>	0,000
<b>Si %</b>	0,000
<b>Mechanical Properties</b>	
<b>Tensile Strength</b>	172,311 N/MM <sup>2</sup>
<b>Yield Strength</b>	305,000 N/MM <sup>2</sup>
<b>Elongation</b>	15.230%
<b>Brinell Hardnessl</b>	84,900 HBW 10/1000

<b>Inner eccentric bushing</b>	
<b>Chemical composition</b>	
<b>Results of elements</b>	
<b>Cu %</b>	77,480
<b>Sn %</b>	7,500
<b>Pb %</b>	14,980
<b>Zn %</b>	0,07
<b>Ni %</b>	0,270
<b>Fe %</b>	0,00
<b>Al %</b>	0,000
<b>Mn %</b>	0,000
<b>Sb %</b>	0,000
<b>P %</b>	0,000
<b>S %</b>	0,000
<b>Si %</b>	0,000
<b>Mechanical Properties</b>	
<b>Tensile Strength</b>	155,230 N/MM <sup>2</sup>
<b>Yield Strength</b>	280,560 N/MM <sup>2</sup>
<b>Elongation</b>	17.150%
<b>Brinell Hardnessl</b>	76,300 HBW 10/1000